

## **Acrylic cibccr coat**

## **Perycryl-Kenzicryl**

### **Product description:**

It is mainly made of special acrylic resins with special pigments and additives. It gives highly attractive glossy appearance with aliphatic isocyanate hardner. It is classified as two component product.

### **Recommended uses:**

The product is recommended as top coat for various metal work applications, vehicles, trucks and for car repairs. It allows high protection for metal surfaces as well high quality appearance.

### **Physical properties:**

Colour	:	as per client request.
Solid content	:	55% as minimum.
Coverage power	:	6-8 m <sup>2</sup> /Kg
Sp. Gravity	:	1.1 g/cm <sup>3</sup> as max. based on colour required
Viscosity	:	120 sec (ford cup no. 4)
Surface dry	:	30 minutes at 25°C
Complete dry	:	1 hour
Mixing ratio	:	2:1:1 (paint-hardner-thinner)
Pot life	:	2 hours

### **Surface preparation:**

Surface should be clean, dry and free from any contaminations. The surface should be treated by suitable methods to allow coated surfaces receiving primer coat to be capable of maximum adhesion.

### **Application methods:**

Being polyurethane coat, To be mixed thoroughly as 2 parts of the paint + 1 part of the hardner + 1 part of the thinner and to be sprayed on the surface which was previously treated by cibccr filler 2k, the 2k filler must be well sanded.

And to be stoved for 30 minutes at 80°C.

### **Storage:**

Product must be stored in accordance with rural regulations. And the storage conditions are to keep the containers in a dry, cool, well-ventilated areas, and away from source of heat and ignition.

### **Packing:**

To be agreed upon with client.

Ready packing:

Kgs 4.00 cans paint+1 Kg hardner+1 Kg thinner

Kgs 20.00 cans paint+5 Kgs hardner+5 Kgs thinner

### **Health And Safety:**

Please observe the precautionary notices displayed on the container. Use under well-ventilated conditions. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Flammable product to be used and stored away from heat sources and naked flames. Do not smoke when using, avoid prolonged inhalation. Observe the general rules governing the use of solvents.

Use protective goggles and gloves, work in well ventilated areas with constant renewal of the air.