

Turbo lacquer

Product description:

It is a paint which is made from an excellent alked resins which gives you a high gloss finish with long gloss retention.

Recommended use:

It is applied on every surface (wood. metal surface and concrete).

Technical information:

Color	:	upon Clint request.
Solid content%	:	60%
Viscosity	:	180 sec according to cup 4 at 25° C.
Appearance	:	high gloss
Film thickness	:	50-70 micron (wet) 35-55 micron (dry)
Application range	:	8:10 m ² /kg for one coat surface.

Application data:

Application method	:	brush or by airless spray.
Mixing ratio	:	5-10% of total weight.
Drying time	:	2 hr (touch dry).
	:	6-8hr (final dry).

Surface preparation:

The surface must be clean and dry from any contamination (dirt or grease) By suitable methods.

Typical recommended paint system:

Cibccr primer : 35 micron (dry film).

Cibccr Matt enamel : 35 micron (dry film).

Cibccr Gloss enamel: 35 micron (dry film).

Storage & packing:

the product must be stored in national regulations avoiding the sun light and keep it in a good ventilations.

Packing:

Upon Clint request.

Health & safety:

Do not breath or inhale mist. avoid skin contact. Spillage on the skin should be immediately be removed with suitable cleaners soap and water. Eyes should be well flushed with water and medical attention sought immediately.